



e.trowel

Product Description

Basic Use: e.trowel is a higher viscosity version of e.roll that is designed to be applied with a trowel. Used for system detailing, repairs, and to create reinforcement details. Reinforcement details use e.trowel and e.poly to reinforce system penetrations, terminations, seams, cracks, and membrane transitions. e.trowel is used on decks, over-excavated walls, blindside vertical walls, and underslab E.Series assemblies. e.trowel can be applied to a wide range of materials/substrates, high density polyethylene (HDPE), polyolefin sheets, geotextile fabric, wood, metal, foam insulation, and concrete based surfaces (green concrete, shotcrete and concrete masonry units (CMU)).

Composition: e.trowel is a high viscosity water-based, polymer-modified anionic asphalt emulsion, which exhibits exceptional bonding, elongation and waterproofing characteristics.

Benefits

- e.trowel is a single component material, no additional blending is required
- Provides the ability to easily detail and repair assemblies without the use of a spray pump
- Non-toxic, non-hazardous, non-flammable, and VOC free
- Forms both a mechanical and ionic bond directly to concrete
- Application to damp substrates is acceptable

Limitations

- Surfaces shall be free of dirt and debris
- Material should be stored above 40°F and not allowed to freeze
- Not a traffic bearing surface, additional protection required
- Must not be applied to ponded water
- Cold temperatures will prolong cure time

Technical Data

Shelf life: 6 months. The ability to apply the product beyond its estimated shelf life is dependent on storage conditions and homogeneity of the product. Storing material in an enclosed temperature controlled environment that maintains a minimum ambient temperature of 65° Fahrenheit will likely extend the shelf life beyond 6 months.

Properties: See physical properties table

Specification Writer: Contact EPRO before writing specifications on this product. E.Series system assemblies should be reviewed in order to meet project specific site conditions.

Installation

Surface Preparation: All surfaces shall be prepared in accordance to manufacturer's specifications. In general, this means all surfaces shall be uniform, free of loose materials, and surface contaminants. Contaminant and loose debris shall be removed prior to application by suitable methods. A test should always be done prior to application using the same cleaning preparation and application procedures to be used on the project.

Application: Please refer to manufacturer's specifications. e.trowel shall be spray applied to the specified nominal mil thickness. e.trowel may be applied by stainless steel trowel.

Availability and Packaging

Contact EPRO sales representative for local distributors or authorized applicators (www.eproinc.com).

e.trowel is available in 5 gallon or 1 gallon containers.

Warranty

Limited Warranty: EPRO Services, Inc. believes to the best of its knowledge that performance tables are accurate and reliable. EPRO warrants this product to be free from defects. EPRO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. EPRO's liability shall be limited in all events to supplying sufficient product to retreat the specific areas to which defective product has been applied. EPRO shall have no other liability, including liability for incidental or resultant damages, whether due to breach of warranty or negligence. This warranty may not be modified or extended by representatives of EPRO or its distributors.

Equipment

No special equipment is necessary.

Technical Services and Information

Complete technical services and information are available by contacting EPRO at 800.882.1896 or www.eproinc.com.

This product was formally known as Ecoline-T.



e.trowel

Typical Physical Properties

Physical Property	Test Method	Value
Color		Brown to Black
Solvent Content.....		No Solvents
Shelf Life.....		1 year
Tensile Strength	ASTM 412	319 psi
Elongation	ASTM 412	300%
Moisture Vapor Transmission.....	ASTM E 96	0.01 g/sq. ft./hr.
Hydrostatic Water Pressure.....	ASTM D 751.....	28 psi
Perm Rating.....	ASTM E 96 (US Perms).....	0.17
Adhesion to Concrete & Masonry	ASTM C 836.....	1 lbf/inch
Crack Bridging.....	ASTM C 836.....	No Cracking
Low Temp. Flexibility.....	ASTM C 836-00.....	No Cracking at -20°C

Packaging: 5 gallon or 1 gallon bucket